

FLAME-RETARDANT, FLEXIBLE FLUORORUBBER COMPOSITION

Patent number: JP62190244
Publication date: 1987-08-20
Inventor: FURUKAWA KIYOSHI; others: 01
Applicant: MITSUBISHI CABLE IND LTD
Classification:
- international: C08L27/12; C08K7/02; C08K9/00; H01B3/44
- european:
Application number: JP19860031522 19860214
Priority number(s):

Report a data error here

Abstract of JP62190244

PURPOSE:A composition having extremely improved tear strength without damaging characteristic rubber properties, obtained by blending fluororubber with fluororesin powder and/or fibrous filler.

CONSTITUTION:(A) 10pts.wt. fluororubber is blended with 5-70pts.wt. (B) fluororesin powder and/or (C) fibrous filler. Tetrafluoroethylene-propylene copolymer is used as the component A. A non-electrically conductive fibrous filler subjected to surface treatment with a coupling agent is used as the component C. Fluororubber having 30-150, especially 50-100 Mooney viscosity at 100 deg.C is preferable as the component A. The component B used has 100µm particle size. Potassium titanate, MOS, etc., is preferable as the component C.

Data supplied from the **esp@cenet** database - Patent Abstracts of Japan